Hangzhou AiBai Chemical Co., Ltd

Factory add:Yipeng Xiaoshan Hangzhou Tel:86-571-22673156 Fax:86-571-83885208 Web:www.xcolorpigment.com

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Printing date: 2015/12/10 Page:1/2 1. Identification of substance and of the company **PIGMENT RED 254** Trade Name: Hangzhou AiBai Chemical Co..Ltd Room 2316, Building 17 Kaiyuan California Sunshine Plaza Xiaoshan Hangzhou China TEL: +86-571-22673158 FAX: +86-571-83885208 2. Composition/Data on components Substance: Pigment Red 254 CAS No: 122390-98-1 EEC Symbol: None **R-Phrases:** None 3. Hazards identification No hazardous effects known The product is not a substance subject to mandatory marking in accordance with the EEC Directive 67/584/EEC Or amendments **First Aid measures** 4. After inhalation: Supply fresh air. After eve contact: Flush with plenty of pressure water for 15 minutes, occasionally raising eye lids. After skin contact: Wash skin with mild soap and water. 5. Fire fighting measures Suitable extinguishing media: no restriction Special hazards caused by the material, its combustion products or resultant gases: none Special personal protection equipment: none 6. Accidental release Environmental protection conduct: Do not sweep or wash into public stretches of water, sewers or sites of unknown discharge paths. After spillage/leakage/gas/ leakage: Clean up immediately with wetting or absorbent material avoiding dusting. 7. Handling and storage Handling: Usual precautions for nuisance dust should be observed. Protection against fire and explosion: The product is non-flammable Storage: Store in roofed places at room temperature Keep containers tightly sealed. Flammability Class: nor applicable. 8. Exposure controls/personal protection Additional notes for design of plants equipment: No farther details, see sec7 Components with workplace-related limits to be monitored: Designation % Type of data Unit 100 Nuisance dust MAK 6 mg/m3 TLV/TWA(USA) 10 mg/m3**Personal protection equipment: Respiratory protection:** An appropriate dust fixer has to be used if a breathable dust liberated.

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Printing date: 2015/12/10	Page:2/2
Trade name: PIGMENT RED 254	
9. <u>Physical and chemical properties</u>	
Appearance: Red powder	Odor: mild
Melting point: 135°C	Relative density:1.56
Decomposition: None Molecular formula: C ₁₈ H ₁₀ Cl ₂ N ₂ O ₂	Flammability: see 7 handling
Tinting strength: $95-105\%$ of the standard	Molecular Weight: 357.19 Volatile matter at 105°C: 2.5%max
Soluble matter in water: 1.0% max	Oil absorption: 40%
Fastness to light:8	Fastness to heat ($^{\circ}$ C):250
Bleeding resistance water: 5	Bleeding resistance linseed oil: 5
Bleeding resistance acid: 5	Bleeding resistance alkalis:5
Bleeding resistance alcohol: 5	Bleeding resistance xylone:5
Bleeding resistance ethyl acetate: 5	Diceding resistance xylone.5
10. <u>Stability and reactivity</u>	
10. <u>Stability and reactivity</u>	
Hazardous decomposition products	
No decomposition at proper storage and application conditions	
11. Toxicological Information	
Because of experience with product mentioned, there are no recognizable hazards for human	
beings, if it is correctly used and applied.	
12. Ecological information	
Avoid filtration into waster draining or soil.	
13. <u>Disposal considerations</u>	
Uses should acquaint themselves with local regulations.	
Disposal is usually carried out by burying at an approved tip or by incineration by a licensed	
waste material processor; stack gases may need to be sorubbed (see section 5 above)	
14. <u>Transport information</u>	
No declaration for transmost required	
No declaration for transport required.	
15. <u>Regulatory information</u>	
Classified according to the Directives 67/548/EEC, and their varions amendments, and labeled	
as below:	
Warning symbols: None	
Warning words: None	
Risk Phrases: None	
Safety Phrases: None	
16. <u>Other information</u>	
Listed in EINECS and TSCA inventories.0	
Intended uses: Paints.	
References: -(1)Occupational Exposure Limits, EH/40(HSE)	
-(2)Deutsche Forschungs gerneinschaft MAK-& BAT-Values.	
-(3)A.C.D.Cowley, Polymers Paint Journal, August 7/21, 1985.	