

Hangzhou Xcolor Chemical Company

Add: Jiangdong Industrial Zone, Xiaoshan District, Hangzhou Tel:86-571-83885088

Fax:86-571-83885208 Web:www.xcolor.net

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Printing date: 2011/01/15 Page:1/2

1. Identification of substance and of the company

Trade Name: PIGMENT YELLOW 14 Hangzhou Xcolor Chemical Company

Add: Jiangdong Industrial Zone, Xiaoshan District, Xiaoshan Hangzhou China

TEL: +86-571-83885088 FAX: +86-571-83885208

2. Composition/Data on components

Substance: Pigment Yellow 14

CAS No: 5408-75-7 EEC Symbol: None R-Phrases: None

3. Hazards identification

No hazardous effects known

The product is not a substance subject to mandatory marking in accordance with the EEC Directive 67/584/EEC Or amendments

4. First Aid measures

After inhalation: Supply fresh air.

After eye contact: Flush with plenty of pressure water for 15 minutes, occasionally raising eye lids.

After skin contact: Wash skin with mild soap and water.

5. Fire fighting measures

Suitable extinguishing media: no restriction

Special hazards caused by the material, its combustion products or resultant gases: none Special personal protection equipment: none

6. Accidental release

Environmental protection conduct: Do mot sweep or wash into public stretches of water, sewers or sites of unknown discharge paths.

After spillage/leakage/gas/ leakage:

Clean up immediately with wetting or absorbent material avoiding dusting.

7. Handling and storage

Handling:

Usual precautions for nuisance dust should be observed.

Protection against fire and explosion:

The product is non-flammable

Storage:

Store in roofed places at room temperature Keep containers tightly sealed.

Flammability Class: nor applicable.

8. Exposure controls/personal protection

Additional notes for design of plants equipment:

No farther details, see sec7

Components with workplace-related limits to be monitored:

Designation	%	Type of data	<u>Unit</u>
Nuisance dust	100	MAK	6 mg/m3
		TLV/TWA(USA)	10 mg/m^3

Personal protection equipment:

Respiratory protection:

An appropriate dust fixer has to be used if a breathable dust liberated.

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Printing date: 2011/01/15 Page:2/2

Trade name: PIGMENT YELLOW 14

9. Physical and chemical properties

Appearance: yellow powder Odor: mild

Melting point: 336°CRelative density: 1.35-1.64Decomposition: NoneFlammability: see 6 handlingMolecular formula: C₃4H₃₀Cl₂N₀O₄Molecular Weight: 657.55

Tinting strength: 95-105% of the standard Volatile matter at 105°C: 2.5% max

Soluble matter in water: 1.5% max

Fastness to light:6

Bleeding resistance water: 5

Oil absorption: 35-45%

Fastness to heat(°C):160

Bleeding resistance linseed oil: 4

Bleeding resistance water: 5
Bleeding resistance acid: 5
Bleeding resistance alcohol: 5
Bleeding resistance alcohol: 5
Bleeding resistance xylone:4
Bleeding resistance xylone:4

10. Stability and reactivity

Hazardous decomposition products

No decomposition at proper storage and application conditions

11. Toxicological Information

Because of experience with product mentioned, there are no recognizable hazards for human beings, if it is correctly used and applied.

12. Ecological information

Avoid filtration into waster draining or soil.

13. <u>Disposal considerations</u>

Uses should acquaint themselves with local regulations.

Disposal is usually carried out by burying at an approved tip or by incineration by a licensed waste material processor; stack gases may need to be sorubbed (see section 5 above)

14. Transport information

No declaration for transport required.

15. Regulatory information

Classified according to the Directives 67/548/EEC, and their varions amendments, and labeled

as below:

Warning symbols: None
Warning words: None
Risk Phrases: None
Safety Phrases: None

16. Other information

Listed in EINECS and TSCA inventories.0

Intended uses: Paints.

References: -(1)Occupational Exposure Limits, EH/40(HSE)

-(2)Deutsche Forschungs gerneinschaft MAK-& BAT-Values. -(3)A.C.D.Cowley, Polymers Paint Journal, August 7/21, 1985.