

# Hangzhou AiBai Chemical Co.,Ltd

## TECHNICAL DATE SHEET

### Fast Yellow K1841

#### Product Description

Color Index	<b>Pigment Yellow 139</b>
C.I. No.	56298
CAS No.	36888-99-0
EC No.	253-256-2
Chemical Family	Isoindoline

#### Technical Properties

Fast Yellow K1841 is a Reddish shade pigment, with excellent kind properties and high luster, high Color Strength.

#### Application

Recommended for PVC, EVA, PS, PC, RUB, fibre.

Suggest for PBT, PA, PO.

#### Physical Date

Density ( g/cm <sup>3</sup> )	1.8
Moisture (%)	≤1.5
Water Soluble Matter (%)	≤1.5
Oil Absorption (ml/100g)	50-60
Electric Conductivity (us/cm)	≤500
Fineness (120mesh)	≤5.0
PH Value	5.0-6.0



Thick Color

Light Color

#### Fastness Properties(5=Execllent, 1=Poor)

Acid Resistance	5
Alkali Resistance	5
Alcohol Resistance	5
Ester Resistance	5
Benzene Resistance	5
Ketone Resistance	5
Soap Resistance	5
Bleeding Resistance	-
Migration Resistance	5
Heat Resistance ( °C )	240
Light Fastness (8=Excellent)	7

Note: The color shade you see in this web is different with the color shade of our products because of effect of monitor, so the color shade is only for your reference.